



Eko-Seal HPPCO® Friction TEST.

**The site was approximately 300 feet in length, A performed multiple tests at 40mph. The site reported an average FN number of 51.1, a high FN of 51.8 and a low FN of 50.4.**

It is our professional opinion that the Eko-Seal HPPCO® has safe and desirable friction values for use on highways.

The Skid Number of the pavement surface is measured using ASTM E 274 “Standard Test Method for Skid Resistance of Paved Surfaces **Using a Full-Scale Tire**”.